

LADRILLO AISLANTE PARA 1260°C



Chemical Analysis(%)	Al ₂ O ₃	37%
	SiO ₂	53%
	Fe ₂ O ₃	1%
	K ₂ O+Na ₂ O	1.3%
Classification Temperature (°C)	(°C)	1250
Bulk Density	Kg/M ³	600
Cold Crushing Strength	MPa	1.2
Thermal Conductivity(W/m.k)	350°C	0.17
	400°C	-
	600°C	-
	1250 °C	-
Permanent Linear Change x24H	%	1200 -0.3
Modulus of Rupture	MPa	1.1
Thermal Expansion(1000°C)	%	0.6